
0830 PCL Cable Ties

Product Specification

(8mm x 300mm)



Properties

General

| Product Code: | 0830-PCL |
|----------------------|-----------------------------|
| Standard Pack Sizes: | Trade bags of 50 |
| Available Colours: | White (Natural, uncoloured) |

Physical

| Nominal Moulded Length: | 296mm |
|--|-------------------------------|
| Width: | 8.0mm [strap] / 14.0mm [head] |
| Thickness: | 2.4mm [strap] / 6.0mm [head] |
| Weight: | 4.7g approx. |
| Maximum Bundle Size: | 75mm diameter |
| Minimum Bundle Size: | <12mm diameter |
| Recommended Maximum Loading when Looped: | 15kg |

Material

| Material: | Polycaprolactone (Ingevity CAPA 6500) |
|-------------------------------|--|
| Density: | 1.15g/cm³ approx. |
| Maximum Tensile Strength: | 15MPa (Yield stress 17MPa, Yield strain 25%) |
| Flexural Modulus: | 400MPa (Shore hardness approx 50D) |
| Resistance to Fuels and Oils: | - |

Thermal


| Low Temperature Brittle Point (Glass Transition): | -60°C |
|---|-----------------|
| Recommended Service Temp Range: | -20°C to +30°C |
| Short Term Peak Temp [no load]: | +45°C |
| Melting Point: | +60°C |
| Notes: | KEEP BELOW 50°C |

Environmental

PCL is digested under ambient conditions by microbes in soil & marine environments via enzymatic hydrolysis. Suitable for aerobic & anaerobic conditions. (Degradation is accelerated in moist, warm conditions.)

| Notes: | DO NOT RECYCLE |
|--------|----------------|
| | |

All data provided for representation only. E&OE.



Rapstrap Ltd., Expo House, Mead Lane, Hertford, Hertfordshire SG13 7AP, UK e: enquiries@rapstrap.com www.rapstrap.com